


BK70AAH

Nickel-Metal Hydride Batteries [Backup for Infrastructure/Standard (H)]

Dimensions



Specifications


| Diameter | | | 14.5 +0 / -0.7 mm |
|--|-----------|--------------|------------------------------------|
| Height | | | 49.0 +0 / -1.5 mm |
| Approximate Weight | | | 18g |
| Nominal Voltage | | | 1.2V |
| Discharge Capacity *1 | | Average *2 | 750 mAh |
| | | Rated (min.) | 700 mAh |
| Approx. Internal Impedance at 1000Hz at charged state. | | | 25 mΩ |
| Charge | | Standard | 70 mA X 16 hrs. |
| | | Rapid *3 | 350 mA X 2.4 hrs. |
| | | Low rate | 35 mA X 32 hrs. 23 mA X 48 hrs. |
| mperature | Charge | Low rate | -10 °C to 60 °C |
| | | Standard | |
| | | Rapid | -10 °C to 45 °C |
| | Discharge | | -10 °C to 60 °C |
| Ambient Temperature | Storage | <1 year | -20 °C to 35 °C |
| | | <6 months | -20 °C to 45 °C |
| | | <1 month | -20 °C to 55 °C |
| | | <1 week | -20 °C to 65 °C |


- *1 After charging at 0.1 It for 16 hours, discharging at 0.2 It.
- 2 For reference only.
- *3 Need specially designed control system. Please contact Panasonic Energy for details

Attention


Battery performance and cycle life are strongly affected by how they are used. In order to maximize battery safety, please consult Panasonic Energy when determining charge/discharge specs, warning label contents and unit design.

Typical charge characteristics





Typical discharge characteristics



Panasonic Energy Co., Ltd.

